

## Wood Grain & Metal Patterns


### Powder Coat Finish



002 Hard Maple



022 Vanilla Ash




003 Douglas Fir



017 American Oak



009 Black Cherry



010 Light Walnut



011 Warm Walnut



021 Oxidized Bronze



020 Scrubbed Walnut



023 Driftwood



016 Barnwood

Colors shown are as accurate as color printing processes permit. Final color selection should be from actual finished color chips. The super durable textured finish comes with a 10 year manufacturer's warranty.

### Performance Characteristics

Substrate	Aluminum
South Florida Weathering 5 years-45 Exposure	Chalk: Rating 8 Color: AAMA 2604 Standard
Salt Spray Resistance ASTM B 117	Hours: 3,000 Field: Rating 8 Scribe: Rating 7, 1/32" - 1/16" (1 - 2 mm)
Humidity ASTM D 2247	Hours: 3,000 Blisters: Rating 8, no more than "few" size No. 8
Pencil Hardness ASTM D 3363	F Minimum

Substrate	Aluminum
Specular Gloss ASTM D 523	20-35 at 60°
Abrasion Resistance ASTM D 968	Coefficient Value > 20 (20 minimum)
Film Adhesion Dry & Wet	No Removal
Direct Impact	No Removal