

## Acrovyn Wall Covering Physical Properties

## TYPICAL PHYSICAL PROPERTIES Acrovyn .040"/.060" WALL COVERING

TEST METHOD	<b>TYPICAL VALUE</b>
ASTM D-792	1.36
ASTM D-638	5,900 psi
ASTM D-256	13 ftlbs./in.
ASTM D-790	9,500 psi
ASTM D-790	330,000 psi
ASTM D-696	.00005 in./in./ºF
ASTM D-785	100
ASTM D-648	165°F
	ASTM D-792 ASTM D-638 ASTM D-256 ASTM D-790 ASTM D-790 ASTM D-696 ASTM D-785