

ABIC TESTING LABORATORIES, INC.

24 Spielman Road
Fairfield, NJ 07004

973-227-7060
Fax: 973-227-0172

To: CS Construction Specialties
Mr. Michael Dance

August 24, 2012

From: Leonard Mackowiak

Subject: Static Coefficient Of Friction Testing
Project No 5418-03b

Introduction

ABIC Testing Laboratories, Inc. was authorized to test the following sample for static coefficient of friction (SCOF). The coefficient of friction determination was made using the James Machine as specified in ASTM D-2047. Testing was conducted using dry and wet neolite.

Flooring Style: G6P Stainless Steel

Results:

<u>Product Identification</u>	<u>Type</u>	<u>SCOF Values</u>	<u>Average SCOF</u>
G6P Stainless Steel	Dry Neolite	.63, .63, .63, .67	.6
		.55, .60, .68, .68	
		.66, .65, .61, .66	
	Wet Neolite	.75, .78, .83, .87	.7
		.74, .74, .73, .73	
		.75, .75, .75, .73	

Discussion

It is generally recognized that a walking surface must have a static coefficient of friction of 0.5 or greater to be considered slip resistant. In our evaluation all of the following material meets this standard:

Flooring Style: G6P Stainless Steel

Respectfully submitted,



Leonard Mackowiak
Vice President